



~~S&S-1102~~
TITLE OF THE INVENTION
**A Process for the Manufacture of a
Disintegrating Roll of an Open-end
Spinning Apparatus as well as a
Disintegrating Roll made by such
a Process**

COPY OF PAPERS
ORIGINALLY FILED

Description
BACKGROUND OF THE INVENTION

The present invention concerns a process in ~~accord with the concept of Claim 1, and~~
~~concerns further~~ a disintegrator roll manufactured by such a process.

In ~~connection with a carding machine~~ DE 25 39 089 A1 discloses a disintegrating roll which has been equipped with a toothed active shredding-element, which displayed a substantial hardness in the top zone of the teeth, but in the foot zone a lesser hardness. In this way an ascertained winding of the toothed shredding-element on the body of the disintegrating roll could be assured. To this purpose, the point of each tooth is a separate element from the foot, and must be bound thereto, for example, by welding. ^{Process} This is a very labor and time intensive procedure ^{and for} and for economic reasons, it cannot be allowed, that such a procedure can be a part of the manufacture of disintegrating rolls for open-end spinning apparatuses, since ~~for a single such carding machine~~ well over a hundred such rolls are required ^{per open-end spinning}.

In accord with another proposal offered by DE 29 04 841 A1, each tooth of the sawtooth shredding-element exhibits a plurality of zones of different hardness, whereby the hardness of the tooth diminishes in the direction from the tooth point to the foot. The tooth foot zone, contrarily, is not hardened, in order to allow for the necessary shaping of the sawtooth wire necessitated by the winding procedure. In order to be able to deform the ends of this sawtooth wire, so that the wire can be securely laid on the roll body, it is necessary to temper these wire ends after the hardening procedure, so that the hardening of the teeth will have no effect on wire ends. The disadvantage of this step is, that it is very difficult to restrict the hardening and subsequent heat treatment to specific areas.

OBJECTS AND SUMMARY OF THE INVENTION

^{The purpose} of the present invention is to propose a process, which enables the wear area of the teeth of a sawtooth wire to be hardened to the greatest degree, preferentially, without simultaneously hardening the foot zone of the teeth ^{A further} and the ^{object} ~~purpose further includes~~ the creation of a process, which, essentially in a simpler and more certain manner, makes possible the installation of the shredding-element, especially

Additional objects and advantages of the invention will be set forth in part in the following description or may be obvious from the description, or may be learned through practice of the invention.

of a sawtooth wire. An additional ^{object} ~~purpose~~ of the invention is to create a disintegrating roll, which can be manufactured with the aid of the aforesaid process. <*

This ^{principal object} ~~purpose~~ is achieved ^{by} ~~by the features of Claim 1~~. Due to the fact that the sawtooth wire is given its essentially final shape before it is mounted on the shredding-element carrier, the hardening, or the hardness provided for the shredding-element in connection with the installation of the shredding-element on a shredding-element carrier, is no longer of such importance, since no consideration need be given to a deformation during the laying of the shredding-element onto a shredding-element carrier.

Advantageously, the sawtooth wire, ⁱⁿ ~~in accord with Claim 2~~ ^{is} ~~is~~ shaped prior to hardening, ^{since} ~~in~~ this manner, the sawtooth wire, when installed on the shredding-element, is subjected to no great stress as compared to the substantial deformation which otherwise would be required.

In a development of the process, ~~in accord with Claim 3~~, provisions can be made, so that the sawtooth wire ^(during the hardening) ~~is to be found~~ ^{remains} on a preshaping body. ^{Further,} whereby this preshaping body, ~~in accord with Claim 4~~, can be constructed by the shredding-element carrier itself.

^{and} ~~More to the purpose,~~ ^{over)} ~~in accord with Claim 5~~, the ends of the sawtooth wire can be subjected to an grinding procedure.

Principally, the hardening of the shredding-element can be carried out in various ways. However, it has shown itself as being advantageous ^{to} ~~to~~ harden the shredding-element by inductive heating ~~in accord with Claim 6, and especially Claims 7 and 8,~~ independently of the shredding-element being sawtooth wire or a combination of needles and at least one saw tooth wire. In this way, the depth to which the hardening of the shredding-element is to be allowed is controllable.

The shredding-element exhibits a relatively small cross section. On this account ^{it} ~~is~~ advantageous, if, in accord with a development of the invented process, ~~which is set forth in Claim 9~~ the formation of oxides, for instance mill scale, is prevented during the hardening process ^{by hardening the shredding element in a protective gas}.

Advantageously, the hardened shredding-element, ~~in accord with Claim 10~~, is subjected to a heat treatment for the avoidance of tensile stresses.

For the elimination of surface unevenness, such as the ~~said~~ mill scale, it is of ^{advantageous to have} ~~advantage~~ of the shredding-element ~~is~~ blasted, ~~in accord with Claim 11 or 12~~, for instance, this can be carried out by glass bead blasting.

Since the material of the shredding-element becomes magnetic, while it is undergoing blasting, the shredding-element is advantageously demagnetized ~~in accord with Claim 13~~. Furthermore, ~~in accord with Claim 14~~, the shredding-element can be deburred.

In spite of the hardening of the shredding-element, it is frequently desirable to further change the surface of the shredding-element which comes into contact with the to-be-^{opened} ~~disintegrated~~ single fibers ^{so that it is} and thereby ~~be~~ suited to the material to be worked. In an advantageous development of the invented process, a coating of the shredding-element can be provided ~~in accord with Claim 15 and possibly Claim 16~~.

In order to prevent ~~that~~ the finally worked-up shredding-element ^{from being} ~~is~~ out of round, the process can be improved in accord with the invention ^{by a further grinding process} ~~in accord with Claim 17, and particularly advantageously improved in accord with Claim 18 and/or 19~~. In particular, by a grinding treatment counter to the direction of the teeth of the saw tooth wire, the goal is advantageously gained wherein scale, which in the operation of the disintegrator roll can lead to non-uniform ^{separation} ~~dissection~~ of fibers, is definitely removed.

The sawtooth wire, before it is brought into its shape, is a non-hardened wire. Thereby, the assurance is given ~~that~~ it permits itself to be brought into the desired shape. Particularly advantageous is the use of a shredding-element carrier of non-hardening material, preferably a low carbon steel, because in this way, the imparting of tension to the shredding-element carrier by the hardening of the shredding-element can be avoided.

In a further advantageous embodiment of the invention, provision ^{are} ~~is~~ made, that the ends of the sawtooth wire, that is, both the wire start and the wire end piece, can be welded to the shredding-element carrier.

Thereby, in a simple and secure way, it can be ^{prevent} ~~prevented~~ ^{from} ~~that~~ the sawtooth wire will ^{loosening} ~~loosen~~ itself from the shredding-element carrier either during hardening or in operation.

As to method of welding, essentially all known methods can be considered. In an advantageous development of the invention, the sawtooth wire is coated ^{in order to} ~~in order to~~ better its abrasion resistance. This coating is done preferably by plasma deposition, for instance, ~~advantageously~~ with titanium nitride. Thereby, it is especially favorable to operate with as low temperatures as possible, so that no hardening loss occurs in the hardened shredding-element wire by the heating of the wire.

With the aid of the previously described process, in accord with the invention, a disintegrating roll can be made ^{with desired attributes} ~~as set forth in Claims 26 to 33~~.

The ~~said~~ roll possesses a hardened shredding-element after it is shaped, that is, after the placement of the shredding-element on the shredding-element carrier. Further, ~~in~~ ^{can be} ~~accord with Claim 28~~ this shredding-element ~~is~~ ^{can be} advantageously, an induction hardened shredding-element. By means of the use of a shredding-element wire and employing a lateral groove at the foot zone of the installed shredding-element carrier, the sawtooth wire can be especially securely fastened on the shredding-element carrier, wherein the sawtooth wire is laid in the ~~said~~ ^{shredding element} groove ^{and by} means of the shaping of the material of the shredding-element carrier, the ~~sawtooth wire~~ ^{shredding element} is pressed into the groove to make a form-fit connection.

The above described process, in accord with the invention, makes possible in a simple and secure manner, an exactly controlled hardening of the shredding-element. ~~(Absent is any danger)~~ when the shredding-element is fitted onto the shredding-element carrier ~~(that the shredding-element will be damaged by this operation)~~ Particularly, when the shredding-element points have been hardened by induction, it is possible by means of high frequency current to limit the hardening to the ~~said~~ points of the shredding-element, while the foot part, held by the shredding-element carrier, remains in its original condition. High frequency hardening, nevertheless, is further advantageous, in that it so hardens those areas of the teeth, which form a hardness transition in each tooth, that, even in the area of the tooth-foot, a hardness is attained, which strongly reduces the attrition in this area of the shredding-element. The shredding-element, or better, its teeth, also have an advantageous uniform rate of wear respectively from the tooth point to the tooth foot.

In this way, the disintegrating rolls can be made with an expectancy of long life, a wear resistant shredding-element, and moreover, operate without risks of breakage or damage to the roll.

Embodiment examples of the invention are explained in the following with the aid of drawings. ~~There is shown in:~~ BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 ~~shows~~ ^{shows} a sawtooth wire which can be manufactured by the invented process in perspective view;

Fig. 2 ~~shows~~ ^{shows} an invented disintegrator roll in profile view, and

Fig. 3 ~~shows~~ ^{shows} a portion sawtooth shredding-element wrapped on a disintegrator roll as well as a grinding wheel section in profile view.

Reference will now be made in detail to the presently preferred embodiments of the invention, one or more of which are shown in the figures. Example is provided to explain the invention, and not as a limitation of the invention. The fact, features illustrated or described as part of one embodiment can be used with another embodiment to yield still a further embodiment. It is intended that the present invention cover such modifications and variations.

DETAILED DESCRIPTION

Where open end spinning is concerned, it is necessary to reduce a ^{sliver} fiber band to individual fibers, which are then fed to an open-end spinning element (not shown) for the production of a continuous ^{yarn} thread. The separation of the fibers by combing from the forward progressing end of the ^{sliver} fiber band, is carried out with the aid of a disintegrator roll 1 enclosed in a housing 4. To execute its designed purpose, the disintegrator roll 4 possesses a specifically designed shredding-element 2 (Fig. 2). To serve as a shredding-element 2, a sawtooth wire 20 is employed (Fig. 1 to 3). On the other hand, there are shredding-elements which, besides one saw tooth wire 20, exhibit still a second such sawtooth wire ~~20~~ (not shown) and/or additionally a plurality of needles.

Because of the combing out of the forward progressing end of the ^{sliver} fiber band, the shredding-element 2 is subjected to a high degree of stress. For this reason, a hardening procedure has been provided for the shredding-element 2. Such a hardening does indeed make the shredding-element 2 hard, but ^{it also} leads to the disadvantage that the shredding-element 2 is made brittle and can be damaged upon the deformation accompanying the fitting of the shredding-element 2 onto a shredding-element carrier 10. Such damage especially occurs in the foot zone 200 (Fig. 3) where fissures can occur.

The shredding-element 10 of the disintegrator roll 1 can be formed by the base body 100 of the disintegrator roll ^{it} 1. However, it is also possible to provide a ring (not shown), which, in a known manner, is held in place by clamps or the like.

In order to avoid the mentioned disadvantages and risks, in accord with the process presented in the following, the flexible, unhardened sawtooth wire shredding-element, which does not yet exhibit any great hardness, ~~(sawtooth wire 20)~~ is first brought into the essentially desired shape, which subsequently, in its installed condition, it will assume on the shredding-element ^{carrier} holder 10. In this way, the desired shape is not brought to the to-be-achieved diameter d, but the spiral shape is additionally considered, which shape the sawtooth wire 20 will assume on the shredding-element carrier on the disintegrator roll.

Principally, the shaping of the sawtooth wire 20 can be done in different ways. Advantageously, however, the sawtooth wire 20 is wound on a shaping body 3 (Fig. 1), the diameter d of which is essentially just as large as the effective diameter D of the shredding-element carrier 10 for the disintegrator roll 1. In this way, it is not required to shape the sawtooth wire in any important degree during its later installation on the shredding-element carrier 10.

The final diameter d , which the sawtooth wire 20 should obtain by the shaping, is not necessarily identical with the outside diameter of the shredding-element carrier 10. As a rule, the sawtooth wire 20 is not wound onto the outside circumference of the shredding-element carrier 10, but rather is received in spiral grooving in this outside circumference of the shredding-element carrier 10 with the result, that the diameter d represents the diameter of this grooving. ^{This} ~~The~~ is plainly ~~to be~~ seen in Fig. 2, in which this effective diameter d of the shredding-element carrier 10 is obviously less than the outside diameter ~~P~~ thereof.

After the sawtooth wire 20 has taken on its desired shape, it is subjected to a hardening procedure. Principally, it is not of great importance, which special hardening procedure is applied (for instance, flame-hardening). Nevertheless, experience shows that it is particularly advantageous, if the hardening of the shredding-element 20 is done by induction. In this process, the depth of the hardening can be exactly determined by a corresponding choice of the frequency of the alternating current.

Since priority is given to having a good hardening on such surfaces as come into contact with the fibers, high frequency currents are particularly well suited for this purpose.

For that reason, the frequency of the alternating current is chosen as high as possible, so that the hardening effect is limited especially to the points 201 of the teeth ^{on} ~~in~~ other words, the hardening is limited to the surface of the teeth of the shredding-element. This comes about at a frequency of the alternating current of at least 1000 kHz, and especially is the case within a frequency range of 1500 and 2000 kHz. The foot area 200 of the sawtooth wire 20 remains unhardened, that is, that area where the teeth are fastened, which is seen in the direction of the shredding-element carrier 10.

The hardening of the sawtooth wire 20 can be carried out after the removal of the same from the preshaping body 30 ^{since} ~~because~~ principally, the preshaped sawtooth wire 20 is conducted through the induced high frequency field of a coil (not shown). In this procedure, the sawtooth wire 20, in the surface area, particularly in the area of the teeth, is highly heated and, after leaving the ~~said~~ field, is chilled.

The process, within the framework of the present invention, can be altered in various ways, especially through the substitution of individual features by equivalents or through other combinations of the features and/or equivalents. Thus, it is not required, that the hardening of the sawtooth wire 20 take place in an unsupported condition.

Much more, the sawtooth wire 20, during this hardening procedure, can still remain on the ~~said~~ preshaping carrier 3. This has the advantage, that the inductive hardening process can be limited, in an especially simple and secure manner to the area of the tooth points 201 to the tooth footings 203, whereby the foot area 200 of the sawtooth wire 20 retains, essentially, its original degree of hardness.

To avoid the manipulation of the sawtooth wire 20 in an already hardened condition, provision can be made in a development of the described process, wherein the sawtooth wire 20 is laid onto the shredding-element carrier just before the carrying out of the hardening procedure and is secured thereon. Then, the so secured sawtooth wire 20 is subjected to a hardening procedure, especially the described induction hardening.

According to an advantageous development of the previously described process, ~~provision can further be made, that~~ the hardening of the shredding-element 2 ^{can be} ~~is~~ carried out under the protection of an inert gas. In this way, ~~it is prevented, that~~ the surface of the sawtooth wire 20, which has been raised to a high temperature during the hardening process, ^{is prevented from reacting to form} ~~reacts~~ with oxygen ~~and~~ rust or scale ~~forms~~, which can lead to undefined conditions and dimensioning of the teeth of the sawtooth wire 20.

Independent of what kind of hardening has been employed, there is created, in accord with the above described process, a disintegrating roll 1 having a sawtooth wire 20, which forms the shredding-element 2. This sawtooth wire, which is only hardened (preferably) inductively, after it has assumed essentially its final shape, and especially after it has been secured to the shredding-element carrier 10.

As part of the hardening procedure, there follows in the customary manner, a chilling of the sawtooth wire 20 by water, oil or the like. Thereby ^{are} ~~is~~ created internally in the sawtooth wire 20 (inner stresses) which can lead to fissuring. In order to avoid these, as soon as possible after the chilling, a heat treatment (tempering) is provided, by means of which such stresses are relieved. In accord with a preferred improvement of the described process, the hardened sawtooth wire 20, during this tempering is brought principally to a temperature of about 130° ^{since} ~~in~~ this way, it is assured, that ~~that~~ the steel, from which the sawtooth wire 20 is made, indeed loses the internal stresses, but not the hardness.

The sawtooth wire 20 which is on the shredding-element carrier 10 is, as a rule, subjected to a grinding procedure since it known from experience, that the sawtooth wire 20 installed on the shredding-element carrier 10 is generally out of round.

In accord with the embodiment depicted in Fig. 3, the disintegrator roll 1, now equipped with the sawtooth wire 20 is driven in the direction of the arrow f_1 , that is, in the direction of the rotation (arrow f_2), in which the disintegrator roll 1 turns during the spinning operation. The sawtooth wire 20, which is driven by the disintegrator roll 1 during the grinding operation then moves contrary to the rotation of a grinding disk 5, which is driven in the direction indicated by the arrow f_3 .

Not only the points 201 of the teeth, but also the ends of the sawtooth wire 20 affixed to the disintegrator roll 1 are subjected to the grinding procedure.

This operation seeks to prevent ~~that~~ ^{from leading to} the ends of the sawtooth wire 20 fastened on the shredding-element 10, ~~could lead~~ in a known manner to later problems with fiber transport within the housing 4.

The hardened shredding-element 2 can still undergo a blasting operation in order to smooth its surface. This ^{blasting} can be done in customary procedures by means of blasting with sand, small glass globules or the like.

Since the shredding-element 2 is magnetized by the blasting procedure, the shredding-element 2 ^(advantageously) after this blasting procedure is demagnetized. This is done, as a rule, by the production of a corresponding magnetic counter field, whereby the shredding-element runs through the hysteresis loop with cyclic reduction of the maximal field strength.

In order to remove and round off protruding spikes and edges of the sawtooth wire 20, it is ^{advantageous} ~~of advantage~~ if the sawtooth wire 20 is deburred. This can be carried out in known chemical procedures in a solution known as appropriate for this purpose, or also electrolytically with the aid of an acid solution.

If desirable, for acquiring certain surface characteristics, the shredding-element can also be coated, for instance, with a galvanically applied nickel plating. In doing this, it is also possible to embed diamond kernels in the nickel layer.

It is also possible ^{to} provide on a shredding-element carrier 10, a shredding element which possesses a sawtooth wire 20 as well as needles (not shown) in combination. Further, instead of a single sawtooth wire 20, ~~also~~ two such sawtooth wires 20 can be laid next to one another, whether the shredding-element 2 has auxiliary needles or not. Independent of the special design of a shredding-element 2 of a disintegrator roll 1, the here described process can be ^{advantageously} ~~always~~ applied with advantage.

It will be appreciated by those skilled in the art that ~~various~~ ^{various} modifications and variations can be made in the present invention without departing from the scope of the invention. It is intended that the present invention include such modifications and variations as come within the scope of the appended claims and their equivalents.

Claims

Claimed is:

1. A process for the production of a disintegrator roll of an open-end spinning apparatus with a shredding-element designed as a sawtooth wire, which is inlaid in a groove of a shredding-element carrier, therein characterized, in that the sawtooth wire ^{being} is converted into a shape, which essentially corresponds to ^{the} that shape ^{that} which the sawtooth wire is to assume on the shredding-element carrier, and the preshaped sawtooth wire ^{being} ~~is to be~~ subsequently hardened. (1) (2)
2. A process in accord with Claim 1, therein characterized, in that the sawtooth wire is preshaped on a preshaping body, the circumference of which is essentially that of the shredding-element carrier of the disintegrator roll. (3)
3. A process in accord with Claim 2, therein characterized, in that the sawtooth wire, during the hardening procedure, remains on the preshaping body.
4. A process in accord with Claim 1, therein characterized, in that the sawtooth wire is shaped by being wound on the shredding-element carrier of the disintegrator roll, and is hardened while it remains on the said shredding-element carrier.
5. A process in accord with one or more of the Claims 1 to 4, therein characterized, in that the ends of the sawtooth wire which are to be found on the shredding-element carrier are subjected to a grinding procedure.
6. A process in accord with one of more of the Claims 1 to 5, therein characterized, in that the shredding-element is hardened by induction.
7. A process in accord with Claim 6, therein characterized, in that the shredding-element is hardened by means of a high frequency current.

8. A process in accord with Claim 7, therein characterized, in that the surface of the shredding element in the area of its teeth is hardened by induction with an alternating current with a frequency of more than 100 kHz, especially with a frequency in a range between 1500 and 2000 kHz.
9. A process in accord with one or more of the Claims 1 to 8, therein characterized, in that the shredding-element is hardened in a protective gas.
10. A process in accord with one or more of the Claims 1 to 9, therein characterized, in that the shredding-element is stress-relieved after the hardening by means of a heat treatment.
11. A process in accord with one or more of the Claims 1 to 10, therein characterized, in that the shredding-element is particle blasted after the hardening.
12. A process in accord with Claim 11, therein characterized, in that the shredding-element is blasted with the aid of glass pearls.
13. A process in accord with one or more of the Claims 1 to 12, therein characterized, in that the shredding-element is demagnetized.
14. A process in accord with one or more of the Claims 1 to 13, therein characterized, in that the shredding-element is chemically deburred.
15. A process in accord with one or more of the Claims 1 to 14, therein characterized, in that the shredding-element is coated.
16. A process in accord with Claim 15, therein characterized, in that the shredding-element is coated by nickel-plating.
17. A process in accord with one or more of the Claims 1 to 16, therein characterized, in that the tooth points of the shredding-element are subjected to a grinding procedure.

18. A process in accord with Claim 17, therein characterized, in that the points of the teeth are subjected to grinding in a direction counter to their operational direction.
19. A process in accord with Claim 18, therein characterized, in that the shredding-element carrier of the disintegrator roll with the affixed sawtooth wire and the grinding disk of the grinding procedure are driven in opposite directions.
20. A process in accord with one or more of the Claims 1 to 19, therein characterized, in that the sawtooth wire, before it is brought into shape, is a non-hardened wire.
21. A process in accord with one or more of the Claims 1 to 20, therein characterized, in that a non-hardening material is used for the shredding-element carrier.
22. A process in accord with Claim 21, therein characterized, in that, as a base material, a low carbon steel is employed.
23. A process in accord with one or more of the Claims 1 to 22, therein characterized, in that the start and/or the end of the sawtooth wire is welded to the shredding-element carrier.
24. A process in accord with one or more of the Claims 1 to 23, therein characterized, in that the sawtooth wire is plasma coated.
25. A process in accord with Claim 24, therein characterized, in that the coating is effected with titanium nitride.
26. A disintegrator roll for an open-end spinning apparatus, wherein the disintegrator roll has been manufactured by one or more of the Claims 1 to 18, with a shredding-element carrier, on which is mounted a sawtooth wire, therein characterized, in that the sawtooth wire (20) is a steel wire at least partially hardened following its shaping.

27. A disintegrator roll in accord with Claim 26, therein characterized, in that the sawtooth wire (20) is a hardened steel wire after being affixed to the shredding-element carrier (10).
28. A disintegrator roll in accord with Claim 26 or 27, therein characterized, in that the shredding-element is constructed as an inductive hardened sawtooth wire (20).
29. A disintegrator roll in accord with one or more of the Claims 26 to 28, therein characterized, in that the shredding-element carrier (10) is made of low carbon steel.
30. A disintegrator roll in accord with one or more of the Claims 26 to 29, therein characterized, in that the start and/or the end of the sawtooth wire (20) is welded to the shredding-element carrier (10).
31. A disintegrator roll in accord with one or more of the Claims 26 to 30, therein characterized, in that the sawtooth wire (20) is plasma coated.
32. A disintegrator roll in accord with Claim 31, therein characterized, in that the sawtooth wire (20) is coated with titanium nitride. 33. A disintegrator roll in accord with one or more of the Claims 26 to 32, therein characterized, in that the sawtooth wire (20) in the foot-area of its teeth occupies a lateral groove.

* * *

ABSTRACT OF THE ~~Summary~~ INVENTION

A sawtooth wire (20) to be laid in a groove of a shredding-element-carrier (22) of a disintegrating roll (24) of an open-end spinning apparatus, is brought into a shape, which essentially represents that shape, which the sawtooth wire (20) is to assume on the said shredding-element carrier (22). The sawtooth wire (20) is preshaped on a dummy body, the circumference of which predominately conforms to that of the shredding-element carrier (22), or the sawtooth wire is directly preshaped on the said shredding-element carrier (22) of the disintegrating roll (24). Only subsequently, is the preshaped sawtooth wire (20) hardened, preferably inductively with the aid of a high frequency alternating current with a frequency of more than 1000 kHz. In this manner, a disintegrating roll (24) is made, the abrasion resistant ^{shredding element} sawtooth wire (20) of which, after the preshaping, i.e., after its securement on the shredding-element carrier (22), is a hardened, especially shredding element inductively hardened steel wire.